

Sax Polymers SAXAMID 226F8 Nylon 6.6, 40% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

Material Notes:

SAXAMID 226F8 is a general purpose polyamide 6.6 injection-molding-grade reinforced with 40% glass fibers. It has very high mechanical strength. Information provided by SAX Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sax-Polymers-SAXAMID-226F8-Nylon-66-40-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	ISO 1183
Viscosity Test	150 cm ³ /g	150 cm ³ /g	H ₂ O ₄ ; ISO 307

Mechanical Properties	Metric	English	Comments
Tensile Strength	225 MPa	32600 psi	5 mm/min; ISO 527-1
Elongation at Break	3.0 %	3.0 %	5 mm/min; ISO 527-1
Tensile Modulus	12.8 GPa	1860 ksi	1 mm/min; ISO 527-1
Flexural Strength	290 MPa	42100 psi	2 mm/min; ISO 178
Flexural Modulus	10.0 GPa	1450 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	13.0 kJ/m ²	6.19 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	16.0 kJ/m ²	7.61 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	88.0 kJ/m ²	41.9 ft-lb/in ²	ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	98.0 kJ/m ²	46.6 ft-lb/in ²	ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	8.40 J/cm ²	40.0 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.30 J/cm ²	44.3 ft-lb/in ²	ISO 179/1eU

Mechanical Properties	Metric @Temperature 23.0 Â°C	English @Temperature 73.4 Â°F	Comments
Charpy Impact, Notched	1.30 J/cmÂ²	6.19 ft-lb/inÂ²	ISO 179/1eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
	1.60 J/cmÂ²	7.61 ft-lb/inÂ²	ISO 179/1eA
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	250 Â°C	482 Â°F	80*10*4 s=60mm; ISO 75-1 a
Vicat Softening Point	255 Â°C	491 Â°F	B/120; ISO 306

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 300 Â°C	536 - 572 Â°F	
Mold Temperature	70.0 - 90.0 Â°C	158 - 194 Â°F	
Drying Temperature	80.0 Â°C	176 Â°F	
	@Time 7200 - 21600 sec	@Time 2.00 - 6.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China