

Sax Polymers SAXLAC 320U Acrylonitrile Butadiene Styrene

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Impact Grade, Molded

Material Notes:

Saxalac 320U is an UV protected, high impact resistant and easy flowing ABS injection molding grade, characterized by good processability and high stiffness. Mechanical property data tested at 50% RH. Information provided by SAX Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sax-Polymers-SAXLAC-320U-Acrylonitrile-Butadiene-Styrene.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	
Melt Flow	20 g/10 min @Load 10.0 kg, Temperature 220 °C	20 g/10 min @Load 22.0 lb, Temperature 428 °F	from MVR; ISO 1033

Mechanical Properties	Metric	English	Comments
Tensile Strength	42.0 MPa	6090 psi	ISO 527-1
Elongation at Break	7.0 %	7.0 %	ISO 527-1
Tensile Modulus	2.20 GPa	319 ksi	ISO 527-1
Izod Impact, Notched (ISO)	10.0 kJ/m ² @Temperature -30.0 °C	4.76 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	25.0 kJ/m ² @Temperature 23.0 °C	11.9 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	100 kJ/m ² @Temperature 23.0 °C	47.6 ft-lb/in ² @Temperature 73.4 °F	ISO 180
	100 kJ/m ² @Temperature -30.0 °C	47.6 ft-lb/in ² @Temperature -22.0 °F	ISO 180
Charpy Impact Unnotched	10.0 J/cm ² @Temperature 23.0 °C	47.6 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
	10.0 J/cm ²	47.6 ft-lb/in ²	ISO 179/1eU

Mechanical Properties	Metric @Temperature -30.0 Â°C	English @Temperature -22.0 Â°F	Comments
Charpy Impact, Notched	1.00 J/cmÂ² @Temperature -30.0 Â°C	4.76 ft-lb/inÂ² @Temperature -22.0 Â°F	ISO 179/1eA
	2.40 J/cmÂ² @Temperature 23.0 Â°C	11.4 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Hot Ball Pressure Test	95.0 Â°C @Thickness 2.00 mm	203 Â°F @Thickness 0.0787 in	IE/CEN 60335-1
Deflection Temperature at 1.8 MPa (264 psi)	82.0 Â°C	180 Â°F	80*10*4 s=60mm; ISO 75-1 a
Vicat Softening Point	95.0 Â°C	203 Â°F	50B; ISO 306
Flammability, UL94	HB	HB	
Glow Wire Test	650 Â°C	1200 Â°F	IE/CEN 60695-2-12

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 260 Â°C	428 - 500 Â°F	
Mold Temperature	60.0 - 90.0 Â°C	140 - 194 Â°F	
Drying Temperature	80.0 Â°C @Time 7200 - 14400 sec	176 Â°F @Time 2.00 - 4.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China