

Schott Glass 8347 Borosilicate Glass

Category : Ceramic , Glass

Material Notes:

Borosilicate glass 3.3 acc. To ISO 3585, chemically and thermally highly resistant, highly UV-transmitting The heavy metal content for the elements lead, cadmium, mercury, and hexavalent chromium is less than 100 ppm Information provided by SCHOTT AG.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-Glass-8347-Borosilicate-Glass.php

Physical Properties	Metric	English	Comments
Density	2.23 g/cc @Temperature 25.0 Â°C	0.0806 lb/inÂ³ @Temperature 77.0 Â°F	

Mechanical Properties	Metric	English	Comments
Modulus of Elasticity	63.0 GPa	9140 ksi	
Poissons Ratio	0.20	0.20	

Thermal Properties	Metric	English	Comments
CTE, linear	3.30 Âµm/m-Â°C @Temperature 20.0 - 300 Â°C	1.83 Âµin/in-Â°F @Temperature 68.0 - 572 Â°F	ISO 7991
Thermal Conductivity	1.20 W/m-K @Temperature 90.0 Â°C	8.33 BTU-in/hr-ftÂ²- Â°F @Temperature 194 Â°F	
Transformation Temperature, Tg	525 Â°C	977 Â°F	ISO 7884-8
Softening Point	825 Â°C	1520 Â°F	Viscosity 10^{7.6} dPa s; ISO 7884-3
Working Point	1260 Â°C	2300 Â°F	Viscosity 10⁴ dPa s; ISO 7884-2
Annealing Point	560 Â°C	1040 Â°F	Viscosity 10¹³ dPa s; ISO 7884-4

Optical Properties	Metric	English	Comments
Refractive Index	1.473 @Wavelength 587.6 nm	1.473 @Wavelength 587.6 nm	
UV Transmittance	<= 70 % @Thickness 1.00 mm,	<= 70 % @Thickness 0.0394 in,	

Optical Properties	Wavelength 254 nm Metric	Wavelength 254 nm English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	3.20e+6 ohm-cm	3.20e+6 ohm-cm	
	@Temperature 350 Â°C	@Temperature 662 Â°F	
	1.00e+8 ohm-cm	1.00e+8 ohm-cm	
	@Temperature 250 Â°C	@Temperature 482 Â°F	
Dielectric Constant	4.6	4.6	
	@Frequency 1.00e+6 Hz, Temperature 25.0 Â°C	@Frequency 1.00e+6 Hz, Temperature 77.0 Â°F	
Dielectric Loss Index	0.0037	0.0037	
	@Frequency 1.00e+6 Hz, Temperature 25.0 Â°C	@Frequency 1.00e+6 Hz, Temperature 77.0 Â°F	

Chemical Properties	Metric	English	Comments
Acid Class, SR	1	1	DIN 12116
Alkali Class, AR	2	2	ISO 695

Descriptive Properties	Value	Comments
Hydrolytic Resistance	Class HGB 1	ISO 719
Stress-optical Coefficient K (10-6mm2N-1)	4	DIN 52314
tk100(Â°C)	250	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China