

Schott LF5 Glass

Category : Ceramic , Glass

Material Notes:

Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-LF5-Glass.php

Physical Properties	Metric	English	Comments
Density	3.22 g/cc	0.116 lb/in ³	

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	450	450	.1/20
Modulus of Elasticity	59.0 GPa	8560 ksi	
Poissons Ratio	0.223	0.223	
Shear Modulus	24.0 GPa	3480 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	9.10 $\mu\text{m/m-}^{\circ}\text{C}$	5.06 $\mu\text{in/in-}^{\circ}\text{F}$	
	@Temperature -30.0 - 70.0 $^{\circ}\text{C}$	@Temperature -22.0 - 158 $^{\circ}\text{F}$	
	10.6 $\mu\text{m/m-}^{\circ}\text{C}$	5.89 $\mu\text{in/in-}^{\circ}\text{F}$	
	@Temperature 20.0 - 300 $^{\circ}\text{C}$	@Temperature 68.0 - 572 $^{\circ}\text{F}$	
Specific Heat Capacity	0.657 J/g- $^{\circ}\text{C}$	0.157 BTU/lb- $^{\circ}\text{F}$	
Thermal Conductivity	0.866 W/m-K	6.01 BTU-in/hr-ft ² - $^{\circ}\text{F}$	
Transformation Temperature, Tg	419 $^{\circ}\text{C}$	786 $^{\circ}\text{F}$	

Optical Properties	Metric	English	Comments
Refractive Index	1.58144	1.58144	n_{d}
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.58482	1.58482	n_{e}
	@Wavelength 546.1 nm	@Wavelength 546.1 nm	
	98.9 %	98.9 %	

Transmission Visible Optical Properties	Metric @Thickness 10.0 mm, Wavelength 380 nm	English @Thickness 0.394 in, Wavelength 380 nm	Comments
	99.7 %	99.7 %	
	@Thickness 10.0 mm, Wavelength 405 nm	@Thickness 0.394 in, Wavelength 405 nm	
	99.8 %	99.8 %	
	@Thickness 10.0 mm, Wavelength 460 nm	@Thickness 0.394 in, Wavelength 460 nm	
	99.9 %	99.9 %	
	@Thickness 10.0 mm, Wavelength 580 nm	@Thickness 0.394 in, Wavelength 580 nm	
	99.9 %	99.9 %	
	@Thickness 10.0 mm, Wavelength 700 nm	@Thickness 0.394 in, Wavelength 700 nm	
IR Transmittance	84.7 %	84.7 %	
	@Thickness 10.0 mm, Wavelength 2325 nm	@Thickness 0.394 in, Wavelength 2325 nm	
	99.7 %	99.7 %	
	@Thickness 10.0 mm, Wavelength 1530 nm	@Thickness 0.394 in, Wavelength 1530 nm	
UV Transmittance	4.0 %	4.0 %	
	@Thickness 10.0 mm, Wavelength 310 nm	@Thickness 0.394 in, Wavelength 310 nm	
	79.9 %	79.9 %	
	@Thickness 10.0 mm, Wavelength 334 nm	@Thickness 0.394 in, Wavelength 334 nm	
	98.4 %	98.4 %	
	@Thickness 10.0 mm, Wavelength 370 nm	@Thickness 0.394 in, Wavelength 370 nm	

Chemical Properties	Metric	English	Comments
Acid Class, SR	1.0	1.0	
Alkali Class, AR	2.3	2.3	
Stain Resistance Class, FR	0.00	0.00	

Descriptive Properties	Value	Comments
B	1	

Climatic Resistance Test CR Descriptive Properties		Value	Comments
HG		2	
K (10-6mm2/N)		2.83	
Phosphate Resistance PR		2	
T1013.0 (Å°C)		411	
T107.6 (Å°C)		585	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China