

Schott N-SF14 Glass

Category : Ceramic , Glass

Material Notes:

Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-N-SF14-Glass.php

Physical Properties	Metric	English	Comments
Density	3.12 g/cc	0.113 lb/in ³	

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	515	515	.1/20
Modulus of Elasticity	88.0 GPa	12800 ksi	
Poissons Ratio	0.259	0.259	
Shear Modulus	35.0 GPa	5080 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	9.40 $\mu\text{m/m-}^{\circ}\text{C}$	5.22 $\mu\text{in/in-}^{\circ}\text{F}$	
	@Temperature -30.0 - 70.0 $^{\circ}\text{C}$	@Temperature -22.0 - 158 $^{\circ}\text{F}$	
	10.9 $\mu\text{m/m-}^{\circ}\text{C}$	6.06 $\mu\text{in/in-}^{\circ}\text{F}$	
	@Temperature 20.0 - 300 $^{\circ}\text{C}$	@Temperature 68.0 - 572 $^{\circ}\text{F}$	
Specific Heat Capacity	0.750 J/g- $^{\circ}\text{C}$	0.179 BTU/lb- $^{\circ}\text{F}$	
Thermal Conductivity	1.00 W/m-K	6.94 BTU-in/hr-ft ² - $^{\circ}\text{F}$	
Transformation Temperature, Tg	566 $^{\circ}\text{C}$	1050 $^{\circ}\text{F}$	

Optical Properties	Metric	English	Comments
Refractive Index	1.76182	1.76182	n_{d}
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.76859	1.76859	n_{e}
	@Wavelength 546.1 nm	@Wavelength 546.1 nm	
	64.2 %	64.2 %	

Transmission Visible Optical Properties	Metric @Thickness 10.0 mm, Wavelength 380 nm	English @Thickness 0.394 in, Wavelength 380 nm	Comments
	91 %	91 %	
	@Thickness 10.0 mm, Wavelength 405 nm	@Thickness 0.394 in, Wavelength 405 nm	
	97.1 %	97.1 %	
	@Thickness 10.0 mm, Wavelength 460 nm	@Thickness 0.394 in, Wavelength 460 nm	
	99.4 %	99.4 %	
	@Thickness 10.0 mm, Wavelength 580 nm	@Thickness 0.394 in, Wavelength 580 nm	
	99.4 %	99.4 %	
	@Thickness 10.0 mm, Wavelength 700 nm	@Thickness 0.394 in, Wavelength 700 nm	
	79.9 %	79.9 %	
	@Thickness 10.0 mm, Wavelength 2500 nm	@Thickness 0.394 in, Wavelength 2500 nm	
IR Transmittance	99.2 %	99.2 %	
	@Thickness 10.0 mm, Wavelength 1530 nm	@Thickness 0.394 in, Wavelength 1530 nm	
	9.5 %	9.5 %	
	@Thickness 10.0 mm, Wavelength 365 nm	@Thickness 0.394 in, Wavelength 365 nm	
	27.6 %	27.6 %	
UV Transmittance	@Thickness 10.0 mm, Wavelength 370 nm	@Thickness 0.394 in, Wavelength 370 nm	

Chemical Properties	Metric	English	Comments
Acid Class, SR	1.0	1.0	
Alkali Class, AR	1.0	1.0	
Stain Resistance Class, FR	0.00	0.00	

Descriptive Properties	Value	Comments
B	0	
Climatic Resistance Test CR	1	
HG	5	

K (10-6mm2/N) Descriptive Properties	2.89 Value	Comments
Phosphate Resistance PR	1	
T1013.0 (Â°C)	562	
T107.6 (Â°C)	657	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China