

Schott P-SK57 Glass

Category : Ceramic , Glass

Material Notes:

Suitable for precision molding Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-P-SK57-Glass.php

Physical Properties	Metric	English	Comments
Density	3.01 g/cc	0.109 lb/in ³	

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	535	535	.1/20
Modulus of Elasticity	93.0 GPa	13500 ksi	
Poissons Ratio	0.249	0.249	
Shear Modulus	37.0 GPa	5370 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	7.20 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	4.00 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature -30.0 - 70.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 158 $\text{Å}^\circ\text{F}$	
	8.90 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	4.94 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 300 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 572 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	0.760 J/g- $\text{Å}^\circ\text{C}$	0.182 BTU/lb- $\text{Å}^\circ\text{F}$	
Thermal Conductivity	1.01 W/m-K	7.01 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$	
Transformation Temperature, Tg	493 $\text{Å}^\circ\text{C}$	919 $\text{Å}^\circ\text{F}$	

Optical Properties	Metric	English	Comments
Refractive Index	1.587	1.587	n_{d}
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.58935	1.58935	n_{e}
	@Wavelength 546.1 nm	@Wavelength 546.1 nm	
	98.9 %	98.9 %	

Transmission Visible Optical Properties	Metric @Thickness 10.0 mm, Wavelength 380 nm	English @Thickness 0.394 in, Wavelength 380 nm	Comments
	99.4 %	99.4 %	
	@Thickness 10.0 mm, Wavelength 405 nm	@Thickness 0.394 in, Wavelength 405 nm	
	99.6 %	99.6 %	
	@Thickness 10.0 mm, Wavelength 460 nm	@Thickness 0.394 in, Wavelength 460 nm	
	99.9 %	99.9 %	
	@Thickness 10.0 mm, Wavelength 580 nm	@Thickness 0.394 in, Wavelength 580 nm	
	99.9 %	99.9 %	
	@Thickness 10.0 mm, Wavelength 700 nm	@Thickness 0.394 in, Wavelength 700 nm	
	69.3 %	69.3 %	
	@Thickness 10.0 mm, Wavelength 2500 nm	@Thickness 0.394 in, Wavelength 2500 nm	
IR Transmittance	99.1 %	99.1 %	
	@Thickness 10.0 mm, Wavelength 1530 nm	@Thickness 0.394 in, Wavelength 1530 nm	
	12.3 %	12.3 %	
	@Thickness 10.0 mm, Wavelength 310 nm	@Thickness 0.394 in, Wavelength 310 nm	
	82.1 %	82.1 %	
UV Transmittance	@Thickness 10.0 mm, Wavelength 334 nm	@Thickness 0.394 in, Wavelength 334 nm	
	98.4 %	98.4 %	
	@Thickness 10.0 mm, Wavelength 370 nm	@Thickness 0.394 in, Wavelength 370 nm	

Chemical Properties	Metric	English	Comments
Acid Class, SR	52.3	52.3	
Alkali Class, AR	2.0	2.0	
Stain Resistance Class, FR	3.0	3.0	

Descriptive Properties	Value	Comments
B	1	

Climatic Resistance Test CR Descriptive Properties		Value	Comments
HG		3	
K (10-6mm2/N)		2.17	
Phosphate Resistance PR		3	
T1013.0 (Å°C)		494	
T107.6 (Å°C)		593	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China