

Shandong Dongyue Shenzhou New Material Co DS2601 Fluoroelastomer Copolymer Gum

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Conformable with: Q/DYS 005-2007
 Brief Introduction:FKM-DS2600 is copolymer of HFP and VDF. Normally it is white or light yellow translucent elastomer whose fluorine content is over 66%. After vulcanizing process, FKM products have excellent mechanical performance, outstanding anti oil property (fuel oil, synthesis oil, lubricating oil) and high thermal stability.
 Main Applications:Widely used in high temperature, aviation, automobile, petroleum and chemical industries, oils, lubricants, etc. Mainly used to produce gaskets, O-rings, V-rings, sealing bowl with metal bone, diaphragms, tube, valve-plate, rolls, etc.
 Properties: Low viscosity, excellent rheological properties
 Application: Additive of high mooney rubber, o-ring, anti-extrusion parts of product
 Information Provided by Shandong Dongyue Shenzhou New Material Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shandong-Dongyue-Shenzhou-New-Material-Co-DS2601-Fluoroelastomer-Copolymer-Gum.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.78 - 1.83 g/cc	1.78 - 1.83 g/cc	
Mooney Viscosity	10 - 29	10 - 29	ML(1+10); DS2601-1
	@Temperature 121 Â°C	@Temperature 250 Â°F	
	30 - 39	30 - 39	ML(1+10); DS2601-2
	@Temperature 121 Â°C	@Temperature 250 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 11.0 MPa	>= 1600 psi	
	>= 9.00 MPa	>= 1310 psi	
Elongation at Break	@Temperature 275 Â°C, Time 86400 sec	@Temperature 527 Â°F, Time 24.0 hour	
	>= 150 %	>= 150 %	
Compression Set	>= 120 %	>= 120 %	AF compression rate 30%
	@Temperature 275 Â°C, Time 86400 sec	@Temperature 527 Â°F, Time 24.0 hour	
	<= 25 %	<= 25 %	
	@Temperature 200 Â°C, Time 86400 sec	@Temperature 392 Â°F, Time 24.0 hour	

Descriptive Properties	Value	Comments
Appearance	White or light yellow translucent rubber piece	

Descriptive Properties	Value	Comments (fuel, 200Å°C, 24h, added weight)
------------------------	-------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China