

Sharadaa Ceramics RECAST LC90 Low Cement Castables

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Description: We bring to our clients a range of Low Cement Castables, that are available in varied alumina content and service range.

Designed for abrasion resistance application, these are widely used in furnaces such as ladle back up lining, sintering furnace roof and soaking pit covers. Information provided by Sharadaa Ceramics Pvt. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sharadaa-Ceramics-RECAST-LC90-Low-Cement-Castables.php

Physical Properties	Metric	English	Comments
Bulk Density	>= 3.00 g/cc	>= 0.108 lb/in ³	Dried at 110Â°C
Grain Size	<= 6000 Åµm	<= 6000 Åµm	

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.0137 GPa	1.99 ksi	
	@Temperature 110 Â°C	@Temperature 230 Â°F	
	0.0196 GPa	2.84 ksi	
	@Temperature 1100 Â°C	@Temperature 2010 Â°F	
	0.0265 GPa	3.84 ksi	
	@Temperature 1500 Â°C	@Temperature 2730 Â°F	
Compressive Strength	98.1 MPa	14200 psi	Cold Crushing
	@Temperature 110 Â°C	@Temperature 230 Â°F	
	113 MPa	16400 psi	Cold Crushing
	@Temperature 1100 Â°C	@Temperature 2010 Â°F	
	127 MPa	18500 psi	Cold Crushing
	@Temperature 1500 Â°C	@Temperature 2730 Â°F	
	24.5 MPa	3560 psi	Cold Crushing
	@Time 86400 sec	@Time 24.0 hour	

Thermal Properties	Metric	English	Comments
	2.32 W/m-K	16.1 BTU-in/hr-ftÂ²-Â°F	

Thermal Properties	Metric	English	Comments
	@ Temperature 600 Â°C, Time 10800 sec	@ Temperature 1110 Â°F, Time 3.00 hour	
	2.56 W/m-K	17.8 BTU-in/hr-ftÂ²- Â°F	
	@ Temperature 400 Â°C, Time 10800 sec	@ Temperature 752 Â°F, Time 3.00 hour	
	2.73 W/m-K	18.9 BTU-in/hr-ftÂ²- Â°F	
	@ Temperature 800 Â°C, Time 10800 sec	@ Temperature 1470 Â°F, Time 3.00 hour	
Maximum Service Temperature, Air	1700 Â°C	3090 Â°F	

Component Elements Properties	Metric	English	Comments
Al2O3	>= 90 %	>= 90 %	
Fe2O3	<= 1.8 %	<= 1.8 %	

Descriptive Properties	Value	Comments
Permanent Linear Change	-0.2 - 0.2%	800Â°C
	-0.3 - 0.3%	1100Â°C
	-0.8 - 0.8%	1500Â°C
Refractoriness	>1820Â°C	
Thermal Expansion	0.85	1000Â°C, Reversible
Water Required to Mix	4 - 5%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China