

Sharadaa Ceramics REFINSUL 13LI Insulating Castables Medium/High Purity

Category : Ceramic

Material Notes:

Description: We offer our clients Insulating Castables that are available in medium as well as high purity. Widely used in various industries, these are renowned for their strength and heat resistance property. Information provided by Sharadaa Ceramics Pvt. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sharadaa-Ceramics-REFINSUL-13LI-Insulating-Castables-MediumHigh-Purity.php

Physical Properties	Metric	English	Comments
Bulk Density	1.45 g/cc	0.0524 lb/in ³	Dried at 110 ^o C
Grain Size	<= 6000 Åµm	<= 6000 Åµm	

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.00490 GPa	0.711 ksi	
	@Temperature 1100 Å°C	@Temperature 2010 Å°F	
	0.00980 GPa	1.42 ksi	
	@Temperature 110 Å°C	@Temperature 230 Å°F	
	0.01177 GPa	1.707 ksi	
	@Temperature 1500 Å°C	@Temperature 2730 Å°F	
Compressive Strength	3.92 MPa	569 psi	Cold Crushing
	@Temperature 1100 Å°C	@Temperature 2010 Å°F	
	3.92 MPa	569 psi	Cold Crushing
	@Temperature 800 Å°C	@Temperature 1470 Å°F	
	4.41 MPa	640 psi	Cold Crushing
	@Temperature 1300 Å°C	@Temperature 2370 Å°F	
	8.34 MPa	1210 psi	Cold Crushing
	@Temperature 110 Å°C	@Temperature 230 Å°F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.465 W/m-K	3.23 BTU-in/hr-ft ² -Å°F	

Thermal Properties	Metric	English	Comments
	0.872 W/m-K	6.05 BTU-in/hr-ftÂ²- Â°F	
	0.930 W/m-K	6.45 BTU-in/hr-ftÂ²- Â°F	

Component Elements Properties	Metric	English	Comments
Fe2O3	1.5 %	1.5 %	

Descriptive Properties	Value	Comments
Permanent Linear Change	<-0.05%	800Â°C
	<-0.08%	1100Â°C
	<-0.3%	1500Â°C
	-0.7 - 0.7%	1300Â°C
Refractoriness	<1900Â°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China