

Shin-Etsu Silicones KE-1311T Silicone, Mold Making RTV

Category : Polymer , Thermoset , Silicone

Material Notes:

Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-1311T-Silicone-Mold-Making-RTV.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	
Viscosity	80000 cP	80000 cP	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	
Tensile Strength at Break	5.86 MPa	850 psi	
Tear Strength	21.9 kN/m	125 pli	

Processing Properties	Metric	English	Comments
Cure Time	1440 min @Temperature 23.0 Â°C	24.0 hour @Temperature 73.4 Â°F	

Descriptive Properties	Value	Comments
Colors	Translucent	
Mix Ratio By Weight	10:01	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China