

Shin-Etsu Silicones KE-3493 Silicone, RTV

Category : Polymer , Thermoset , Silicone

Material Notes:

Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-3493-Silicone-RTV.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	
Tensile Strength	1.50 MPa	218 psi	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.60 W/m-K	11.1 BTU-in/hr-ft ² - °F	

Processing Properties	Metric	English	Comments
Cure Time	3.00 min	0.0500 hour	Tack Free Time

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China