

Shin-Etsu Silicones KEG-2000-30A/B Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

KEG-2000-30 is a liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. It's viscosity is low enough to allow easy pumping through most injection molding systems. Features Rapid cure time at elevated temperature Long pot life at room temperature Applications O-rings Diaphragms Capping Rubber rollers Connector packings Other electrical parts Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KEG-2000-30AB-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	32	32	
Tensile Strength	8.501 MPa	1233 psi	
Elongation at Yield	750 %	750 %	
100% Modulus	0.000703 GPa	0.102 ksi	
Tear Strength	25.1 kN/m	143 pli	
Compression Set	6.0 % @Temperature 180 Â°C, Time 79200 sec	6.0 % @Temperature 356 Â°F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	240 min @Temperature 200 Â°C	4.00 hour @Temperature 392 Â°F	Post Cure

Descriptive Properties	Value	Comments
Regulatory Testing	Class VI, FDA	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China