

Shin-Etsu Silicones LIMSâ„¢ KE1950-30A/B Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

KE-1950-30 is a liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. It's viscosity is low enough to allow easy pumping through most injection molding systems.FeaturesRapid cure time at elevated temperatureLong pot life at room temperatureApplicationsO-ringsDiaphragmsCappingRubber rollersConnector packingsOther electrical partsInformation Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:
http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-LIMS-KE1950-30AB-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	
Viscosity	250000 cP	250000 cP	B
	250000 cP	250000 cP	A
Linear Mold Shrinkage	0.020 cm/cm	0.020 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	32	32	
Tensile Strength	8.80 MPa	1280 psi	
Elongation at Yield	700 %	700 %	
100% Modulus	0.000696 GPa	0.101 ksi	
Tear Strength	25.0 kN/m	143 pli	
Compression Set	6.0 % @Temperature 200 Â°C, Time 14400 sec	6.0 % @Temperature 392 Â°F, Time 4.00 hour	
	22 % @Temperature 150 Â°C, Time 3600 sec	22 % @Temperature 302 Â°F, Time 1.00 hour	

Processing Properties	Metric	English	Comments
Cure Time	5.00 min @Temperature 120 Â°C	0.0833 hour @Temperature 248 Â°F	Press Cure
	60.0 min @Temperature 150 Â°C	1.00 hour @Temperature 302 Â°F	Post Cure

Processing Properties	Metric	English	Comments
Descriptive Properties	Value		Comments
Appearance	Translucent		
Cure Rate	29		T10 (302Â°F, ODR)
	39		T90 (302Â°F, ODR)
Regulatory Testing	Class VI, FDA		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China