

Shin-Etsu Silicones LIMSâ„¢ KEG2000-60A/B Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

KEG2000-60 is a liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. Its viscosity is low enough to allow easy pumping through most injection molding systems.FeaturesHigh tear strengthRapid cure time at elevated temperatureLong pot life at room temperatureApplicationsO-Rings Diaphragms CappingRubber rollersConnector packagingOther electrical partsInformation Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:
http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-LIMS-KEG2000-60AB-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	
Viscosity	1.60e+6 cP	1.60e+6 cP	A
	1.60e+6 cP	1.60e+6 cP	B
Linear Mold Shrinkage	0.026 cm/cm	0.026 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	
Tensile Strength	10.5 MPa	1520 psi	
Elongation at Yield	470 %	470 %	
100% Modulus	0.00246 GPa	0.357 ksi	
Tear Strength	45.0 kN/m	257 pli	
Compression Set	9.0 %	9.0 %	
	@Temperature 200 Â°C, Time 14400 sec	@Temperature 392 Â°F, Time 4.00 hour	
	38 %	38 %	
	@Temperature 150 Â°C, Time 3600 sec	@Temperature 302 Â°F, Time 1.00 hour	

Processing Properties	Metric	English	Comments
Cure Time	5.00 min	0.0833 hour	Press Cure
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	60.0 min	1.00 hour	Post Cure
	@Temperature 150 Â°C	@Temperature 302 Â°F	

Processing Properties	Metric	English	Comments
Descriptive Properties	Value		Comments
Appearance	Translucent		
Cure Rate	35		T10 (302Â°F, ODR)
	48		T90 (302Â°F, ODR)
Regulatory Testing	Class VI, FDA		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China