

Shinkong Synthetic Fibers Shinite® C501G15 Nylon 6, 15% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 20% Glass Fiber Filled

Material Notes:

Information from Shinkong Synthetic Fibers Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shinkong-Synthetic-Fibers-Shinite-C501G15-Nylon-6-15-Glass-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Water Absorption	1.3 %	1.3 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0050 - 0.0090 cm/cm	0.0050 - 0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	93.2 MPa	13500 psi	ASTM D638
Elongation at Break	3.4 %	3.4 %	ASTM D638
Flexural Yield Strength	147 MPa	21300 psi	ASTM D790
Flexural Modulus	4.90 GPa	711 ksi	ASTM D790
Izod Impact, Notched	0.637 J/cm @Thickness 3.17 mm, Temperature 23.0 °C	1.19 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China