

Shinkong Synthetic Fibers Shinite® T101 PET

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET)

Material Notes:

Information from Shinkong Synthetic Fibers Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shinkong-Synthetic-Fibers-Shinite-T101-PET.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	ASTM D792
Water Absorption	0.090 %	0.090 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0080 - 0.020 cm/cm	0.0080 - 0.020 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0080 - 0.020 cm/cm	0.0080 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	49.0 MPa	7110 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Flexural Yield Strength	83.4 MPa	12100 psi	ASTM D790
Flexural Modulus	2.45 GPa	356 ksi	ASTM D790
Izod Impact, Notched	0.294 J/cm @Thickness 3.17 mm, Temperature 23.0 Â°C	0.551 ft-lb/in @Thickness 0.125 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	60.0 Â°C	140 Â°F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.0	3.0	ASTM D150
Dielectric Strength	15.0 kV/mm	381 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China