

Sibur ABS 0809 Molding Grade ABS Plastic

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

With high thermal stability and rigidity for small automobile products and working under higher temperatures.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-ABS-0809-Molding-Grade-ABS-Plastic.php

Physical Properties	Metric	English	Comments
Water Absorption	<= 0.30 %	<= 0.30 %	
Melt Index of Compound	2.5 - 5.5 g/10 min	2.5 - 5.5 g/10 min	

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched (ISO)	>= 8.80 kJ/mÂ²	>= 4.19 ft-lb/inÂ²	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	106 Â°C	223 Â°F	Deflection temperature in bending , load unknown
Vicat Softening Point	<= 106 Â°C	<= 223 Â°F	

Chemical Properties	Metric	English	Comments
Styrene Content	<= 0.050 %	<= 0.050 %	

Descriptive Properties	Value	Comments
Acrylonitrile Content	<.001	
Impact Tension Strength	>8.8 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China