

## Sibur ABS 1530 Molding Grade ABS Plastic

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

### Material Notes:

Thermal resistance with higher fluidity for large and thin wall articles.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sibur-ABS-1530-Molding-Grade-ABS-Plastic.php](http://www.lookpolymers.com/polymer_Sibur-ABS-1530-Molding-Grade-ABS-Plastic.php)

| Physical Properties    | Metric           | English          | Comments       |
|------------------------|------------------|------------------|----------------|
| Water Absorption       | <= 0.30 %        | <= 0.30 %        |                |
| Melt Index of Compound | 10 - 12 g/10 min | 10 - 12 g/10 min | II Preparation |
|                        | 10 - 17 g/10 min | 10 - 17 g/10 min |                |

| Mechanical Properties      | Metric         | English            | Comments |
|----------------------------|----------------|--------------------|----------|
| Elongation at Break        | >= 13 %        | >= 13 %            |          |
| Izod Impact, Notched (ISO) | >= 19.6 kJ/mÂ² | >= 9.33 ft-lb/inÂ² |          |

| Thermal Properties    | Metric      | English    | Comments |
|-----------------------|-------------|------------|----------|
| Vicat Softening Point | <= 90.0 Â°C | <= 194 Â°F |          |

| Descriptive Properties  | Value     | Comments |
|-------------------------|-----------|----------|
| Impact Tension Strength | >34.3 MPa |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China