

Sibur DST-45 RM Styrene-Butadiene-Styrene Block Copolymer (SBS-TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrene-Butadiene , Styrene/Butadiene/Styrene (SBS)

Material Notes:

Kraton D 4271. For production of footwear compositions.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-DST-45-RM-Styrene-Butadiene-Styrene-Block-Copolymer-SBS-TPE.php

Physical Properties	Metric	English	Comments
Melt Index of Compound	2.0 - 9.0 g/10 min @Temperature 190 Â°C	2.0 - 9.0 g/10 min @Temperature 374 Â°F	P=49, 1 H

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	
Tensile Strength at Break	>= 11.8 MPa	>= 1710 psi	
Elongation at Break	>= 930 %	>= 930 %	

Chemical Properties	Metric	English	Comments
Styrene Content	43 - 47 %	43 - 47 %	

Descriptive Properties	Value	Comments
Loss During Drying	<0.5%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China