

Sibur SKI-3S Superior Quality, 2nd Group Isoprene Rubber (IR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Nipol-IR 2200, Natsyn-2200, Kraton-IR 401. It is used instead of natural rubber during production of colored rubber articles, medical articles, and rubbers contacting with food products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-SKI-3S-Superior-Quality-2nd-Group-Isoprene-Rubber-IR.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	61 - 71	61 - 71	ML 1-4
	@Temperature 100 Â°C	@Temperature 212 Â°F	
Ash	<= 0.50 %	<= 0.50 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 30.4 MPa	>= 4410 psi	
Tensile Strength, Ultimate	>= 21.6 MPa	>= 3130 psi	
	@Temperature 100 Â°C	@Temperature 212 Â°F	

Descriptive Properties	Value	Comments
Loss During Drying	<1.2%	
Mass Share Adigol-2	0.2-0.6%	
Mass Share Agidol-1	0.5-1.3%	
Mass Share Lavinox 22M-46	0.2-0.6%	
Mass Share Ralox-46	0.2-0.6%	
Spread Flow Batch Error	<Â±8 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China