

Sibur SKS-30 ARKM-15 2nd Group Oil-Filled Styrene-Butadiene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

SBR 1705. For use in the tire industry for production of tire thread and other parts for tires, in the rubber technical industry for production of a wide assortment of rubber technical articles, and in the shoe industry for production of white and colored footwear.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-SKS-30-ARKM-15-2nd-Group-Oil-Filled-Styrene-Butadiene-Rubber.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	45 - 54	45 - 54	ML 1-4
	@Temperature 100 Â°C	@Temperature 212 Â°F	
Ash	<= 0.60 %	<= 0.60 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 24.5 MPa	>= 3550 psi	
Elongation at Break	550 - 750 %	550 - 750 %	

Chemical Properties	Metric	English	Comments
Styrene Content	22 - 25 %	22 - 25 %	

Descriptive Properties	Value	Comments
Loss During Drying	<0.4%	
Mass Share Adigol-2	0.6-1.2	
Mass Share of A-Methyl Styrene	21-24%	
Mass Share of Oil	14.5-17%	
Mass Share of P-23	0.6-1.2	
Mass Share of VS-1	0.15-0.35	
Mass Share of VS-30A	1-2	
Mass Share of VTS-150	1-1.5	
Spread Flow Batch Error	<Â±8 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China