

Sichuan Deyang Haton® hGR20 Polyphenylene Sulfide, Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 20% Glass Fiber Filler

Material Notes:

Injection molding Information provided by Sichuan Deyang Chemical Co., LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sichuan-Deyang-Haton-hGR20-Polyphenylene-Sulfide-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	GB/T 1033.1-2008
Water Absorption	0.020 %	0.020 %	GB/T 1034-2008
Linear Mold Shrinkage, Flow	0.0025 cm/cm	0.0025 in/in	GB/T 15585-1995
Linear Mold Shrinkage, Transverse	0.0075 cm/cm	0.0075 in/in	GB/T 15585-1995

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	102	102	GB/T 3398.2-2008
Tensile Strength	130 MPa	18900 psi	GB/T 1040.2-2006
Elongation at Break	1.8 %	1.8 %	GB/T 1040.2-2006
Flexural Strength	190 MPa	27600 psi	GB/T 9341-2008
Flexural Modulus	9.10 GPa	1320 ksi	GB/T 9341-2008
Izod Impact, Notched (ISO)	9.60 kJ/m ²	4.57 ft-lb/in ²	GB/T 1843-2008

Thermal Properties	Metric	English	Comments
Melting Point	280 Â°C	536 Â°F	GBT/T 19466.3-2004
Deflection Temperature at 1.8 MPa (264 psi)	265 Â°C	509 Â°F	GB/T 1634.2-2004
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.20e+16 ohm-cm	2.20e+16 ohm-cm	GB/T1410-2006
Surface Resistivity per Square	9.80e+15 ohm	9.80e+15 ohm	GB/T1410-2006
Dielectric Constant	3.2	3.2	GB/T 1409-2006
Dielectric Strength	16.0 kV/mm	406 kV/in	GB/T1408.1-2006

Designation Factor Electrical Properties	0.0020 Metric	0.0020 English	GB/T 1409-2006 Comments
---	------------------	-------------------	----------------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China