

Silikony Polskie Gumosil T Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Hard, resistant to sudden and extensive temperature changes

Order this product through the following link:

http://www.lookpolymers.com/polymer_Silikony-Polskie-Gumosil-T-Silicone-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	Before Curing
Viscosity	25000 cP	25000 cP	Before Curing
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	After Curing

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	After Curing
Tensile Strength at Break	3.00 MPa	435 psi	After Curing
Elongation at Break	150 %	150 %	After Curing

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	300 Â°C	572 Â°F	

Processing Properties	Metric	English	Comments
Cure Time	<= 1440 min	<= 24.0 hour	Curing
Pot Life	30 min	30 min	Curing

Descriptive Properties	Value	Comments
Color	Red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China