

Skamol Group Moler 10 Aggregate Insulation

Category : Ceramic , Oxide , Silicon Oxide

Material Notes:

SKAMOL insulating aggregates have the following characteristics: Max. service temperature: Up to 900°C (1652°F) Back-up insulation Lightweight Good insulating properties Chemically inert Due to free-flowing properties Moler aggregates are ideally suitable as a loose-fill insulation for furnace cavities and double skin linings, over arched roofs and in open joints, leveling of furnace bottoms and hearths. Information provided by Skamol.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Skamol-Group-Moler-10-Aggregate-Insulation.php

Physical Properties	Metric	English	Comments
Bulk Density	0.449 g/cc	0.0162 lb/in ³	As Supplied
Loss On Ignition	1.50 % @Temperature 1025 °C	1.50 % @Temperature 1877 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.160 W/m-K @Temperature 200 °C	1.11 BTU-in/hr-ft ² - °F @Temperature 392 °F	Mean temp.; BS 1902 Section 5.5 1991
	0.180 W/m-K @Temperature 400 °C	1.25 BTU-in/hr-ft ² - °F @Temperature 752 °F	BS 1902 Section 5.5 1991
	0.200 W/m-K @Temperature 600 °C	1.39 BTU-in/hr-ft ² - °F @Temperature 1110 °F	BS 1902 Section 5.5 1991
Maximum Service Temperature, Air	900 °C	1650 °F	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	9.0 %	9.0 %	
CaO	0.80 %	0.80 %	
Fe ₂ O ₃	7.0 %	7.0 %	
K ₂ O	1.6 %	1.6 %	
MgO	1.3 %	1.3 %	
Na ₂ O	0.40 %	0.40 %	

Component Elements Properties	Metric	English	Comments
SIO2	Wt%	Wt%	
S03	1.2 %	1.2 %	
TiO2	0.70 %	0.70 %	

Descriptive Properties	Value	Comments
Color	Red-Brown	
Pyrometric Cone Equivalent	1350Â°C	ASTM C24-89, ORTON cones

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China