

Skamol Group VERMICAST 116-25 Insulating Castable

Category : Ceramic , Oxide

Material Notes:

SKAMOL insulating castables have the following characteristics: Max. service temperature: Up to 1100Â°C (2102Â°F) Back-up insulation or hot-face uses For casting and gunning Products are based on fired Moler aggregates, refractory materials, or exfoliated vermiculite Effective insulation Quick and economical installation Used as monolithic heat insulation in a wide range of industrial kilns and furnaces, boilers, chimneys, and flues The Vermicast grades are favored as infill in aluminum reduction cell cathodes due to their non-wetting capacity to molten metal and good bath resistance. Information provided by Skamol.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Skamol-Group-VERMICAST-116-25-Insulating-Castable.php

Physical Properties	Metric	English	Comments
Bulk Density	0.208 g/cc	0.00752 lb/inÂ³	As Supplied
	0.304 g/cc	0.0110 lb/inÂ³	Defined by casting method, +/- 50kg (110 lbs)
Loss On Ignition	6.00 %	6.00 %	
	@Temperature 1025 Â°C	@Temperature 1877 Â°F	
Porosity	89 %	89 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	0.300 MPa	43.5 psi	Dried at 110Â°C (230Â°F)

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.130 W/m-K	0.902 BTU-in/hr-ftÂ²-Â°F	Mean temp.; ASTMÂ C-201 supplemented by ASTM C-182
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	0.150 W/m-K	1.04 BTU-in/hr-ftÂ²-Â°F	ASTMÂ C-201 supplemented by ASTM C-182
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	0.180 W/m-K	1.25 BTU-in/hr-ftÂ²-Â°F	ASTMÂ C-201 supplemented by ASTM C-182
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
Maximum Service Temperature, Air	1050 Â°C	1920 Â°F	
Shrinkage	1.50 %	1.50 %	Linear Reheat Shrinkage, 12h at 100Â°C (180Â°F) below max. service temp.
	@Time 43200 sec	@Time 12.0 hour	

Thermal Properties	Metric	English	Comments
Component Elements Properties	Metric	English	Comments
Al2O3 + TiO2	16 %	16 %	
CaO	22 %	22 %	
Fe2O3	7.0 %	7.0 %	
K2O+Na2O	4.5 %	4.5 %	
MgO	10 %	10 %	
SiO2	34 %	34 %	

Descriptive Properties	Value	Comments
Pyrometric Cone Equivalent	1310Â°C	ASTM C24-89, ORTON cones

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China