

Solvay RHODOLINE® 697 Surfactant

Category: Fluid

Material Notes:

Description: Highly efficient mineral oil based defoamers for flat to gloss paints, quick process foam know down and high in-can persistency. Identification: OIL BASE DEFOAMERAvailable in: North America Applications: RHODOLINE® 697 is a defoamer especially formulated to give outstanding foam control when used in the manufacture of paints and coatings. In paint formulations, 2- 6 pounds of RHODOLINE® 697 will effectively defoam 100 gallons of paint, providing prolonged protection. RHODOLINE® 697 is not water-dispersible and should be used as received. For easy handling, RHODOLINE® 697 should be stored at temperatures above 50°F, but not above 100°F. Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-RHODOLINE-697-Surfactant.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------|------------------------|-------------------------|
| Density | 0.840 - 0.980 g/cc | 0.0303 - 0.0354 lb/in³ | RP-17617 |
| рН | 7.0 | 7.0 | 0.05 |
| Viscosity | 800 - 1200 cP | 800 - 1200 cP | #3 sp @ 60 rpm; RP-0596 |
| Ash | 2.0 - 2.5 % | 2.0 - 2.5 % | RP-0065 |

| Processing Properties | Metric | English | Comments |
|-----------------------|------------|------------|----------|
| Shelf Life | 24.0 Month | 24.0 Month | |

| Descriptive Properties | Value | Comments |
|------------------------|-----------------------------------|----------------|
| Appearance | Opaque, White to Off-White Liquid | RP-0064 |
| Hegman Test | <6 | Grind, RP-9186 |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China