

Solvay Specialty Polymers FOMBLIN® LC200 PFPE Lubricant

Category : Fluid , Lubricant , Perfluoropolyether (PFPE)

Material Notes:

FOMBLIN LC perfluoropolyether fluids have the following unique features: excellent wear characteristics; very good low temperature properties; cost-effective; and outstanding for applications requiring low viscosity. Information provided by Solvay Solexis, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-FOMBLIN-LC200-PFPE-Lubricant.php

Physical Properties	Metric	English	Comments
Density	1.89 g/cc	0.0683 lb/in ³	ASTM D891
Viscosity Measurement	122	122	Viscosity Index; ASTM D2270
Kinematic Viscosity	190 cSt @Temperature 20.0 °C	190 cSt @Temperature 68.0 °F	ASTM D445
Kinematic Viscosity at 40°C (104°F)	65.6 cSt	65.6 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	9.4 cSt	9.4 cSt	ASTM D445
Molecular Weight	2900 g/mol	2900 g/mol	
Evaporation Loss	1.7 %	1.7 %	22 hrs. at 60°C; ASTM 2595
	17 %	17 %	22 hrs. at 120°C; ASTM 2595

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	105 kg	232 lb (mass)	Mean Hertz Load; IP 239
	400 kg	882 lb (mass)	Welding Load; IP 239
Four Ball Wear	0.700 mm	0.0276 in	Avg. scar diameter; ASTM D4172

Thermal Properties	Metric	English	Comments
Pour Point	-40.0 °C	-40.0 °F	ASTM D97

Descriptive Properties	Value	Comments
Approximate ISO Grade	68	
Oxygen Impact (BAM) 100°C, Impact Pressure	180 atm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China