

Solvay Specialty Polymers Primef® 7002 Polyphenylene Sulfide (PPS), 65% GlassMineral (discontinued **)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS), Mineral/Glass-Fiber Filled

Material Notes:

Primef 7002 is a 65% mineral/glass fiber reinforced polyphenylene sulfide (PPS). This grade offers higher fluidity than Primef 7010 (also 65% mineral/glass fiber), but with somewhat lower mechanical properties. In general, PPS offers an excellent balance of properties including high temperature resistance, chemical resistance, dimensional stability and electrical characteristics. Because of its inherent flame retardancy, PPS is a good choice for high-temperature electrical and electronic applications. Features: Flame Retardant; Good Chemical Resistance; Good Creep Resistance; Good Dimensional Stability; Good Processability; High Flow; High Heat Resistance; Low to No Water Absorption Uses: Availability: Europe Holding Time: 3 sec Cooling Time, 2 mm: 2.5 sec Information provide by Solvay Specialty Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Primef-7002-Polyphenylene-Sulfide-PPS-65-GlassMineral-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.96 g/cc	0.0708 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	160 MPa	23200 psi	ISO 527-2
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Elongation at Break	1.2 %	1.2 %	ISO 527-2
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Modulus	20.0 GPa	2900 ksi	ISO 527-2
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Strength	240 MPa	34800 psi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Modulus	21.0 GPa	3050 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.50 J/cm	4.68 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.600 W/m-K	4.16 BTU-in/hr-ft ² -°F	ISO 8302

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 °C	428 °F	ASTM D794
Deflection Temperature at 1.8 MPa (264 psi)	>= 260 °C	>= 500 °F	ISO 75-2/A
Flammability, UL94	V-0	V-0	
	@Thickness 0.800 mm	@Thickness 0.0315 in	
Oxygen Index	58 %	58 %	ISO 4598-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	4.9	4.9	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	5.0	5.0	IEC 60250
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dielectric Strength	15.0 kV/mm	381 kV/in	IEC 60243-1
Dissipation Factor	0.0090	0.0090	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.030	0.030	IEC 60250
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Comparative Tracking Index	200 V	200 V	IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	290 - 300 °C	554 - 572 °F	
Middle Barrel Temperature	310 - 320 °C	590 - 608 °F	
Front Barrel Temperature	320 - 330 °C	608 - 626 °F	
Nozzle Temperature	320 - 350 °C	608 - 662 °F	
Melt Temperature	320 - 330 °C	608 - 626 °F	
Mold Temperature	150 - 160 °C	302 - 320 °F	
Injection Pressure	50.0 - 150 MPa	7250 - 21800 psi	
Hold Pressure	30.0 - 150 MPa	4350 - 21800 psi	
Back Pressure	0.000 - 1.00 MPa	0.000 - 145 psi	

Processing Properties	Metric	English	Comments
Screw Speed	3.0 ~ 10 rpm	3.0 ~ 10 rpm	

Descriptive Properties	Value	Comments
Additional Properties	Spiral Flow Length - Internal Method: 150 mm	
Forms	Pellets	
Injection Rate	Fast	
Processing Method	Injection Molding	
RoHS Compliance	RoHS Compliant	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China