

## Solvay Specialty Polymers Radel® R-7625 Polyphenylsulfone (PPSU)

Category : Polymer , Thermoplastic , Polyphenylsulfone (PPSU)

### Material Notes:

Radel® R-7625 polyphenylsulfone resin is a cost-effective solution for aircraft interior applications that offers improved UV resistance versus Radel® R-7535 and Radel® R-7558. The product complies with the FAA regulation 14CFR Part 25 Appendix F, offering vertical burn resistance, very low smoke generation and, through the use of proprietary additives, low heat release values, when tested using the Ohio State University (OSU) rate of heat release method. It also generates low flaming-mode toxic gas emissions. Features: Detergent Resistant; Flame Retardant; Good Flow; Good Processing Stability; Good Toughness; Low Smoke Emission; Low Toxicity Uses: Aerospace Applications; Aircraft Applications; Aircraft Interiors Additional Properties: OSU Peak Heat Release Rate - FAR 25, AppF < 55.0 kW/m<sup>2</sup>; OSU Total Heat Release - FAR 25, AppF < 20.0 kW·min/m<sup>2</sup>; Smoke Density - FAR 25, AppF < 5.0; Vertical Burn - 60 second - FAR 25, AppF No Drip sec; Vertical Burn - 60 second - FAR 25, AppF 0.0 hr; Vertical Burn - 60 second - FAR 25, AppF < 7.62 cm Information provided by Solvay Specialty Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Solvay-Specialty-Polymers-Radel-R-7625-Polyphenylsulfone-PPSU.php](http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Radel-R-7625-Polyphenylsulfone-PPSU.php)

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.30 % @Time 86400 sec	0.30 % @Time 24.0 hour	ISO 62
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	
Melt Flow	17 g/10 min @Load 2.16 kg, Temperature 380 °C	17 g/10 min @Load 4.76 lb, Temperature 716 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	86.2 MPa	12500 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Tensile Modulus	2.83 GPa	410 ksi	ASTM D638
Flexural Strength	121 MPa	17500 psi	ASTM D790
Flexural Modulus	2.76 GPa	400 ksi	ASTM D790
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	193 °C	379 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	354 - 371 Å°C	669 - 700 Å°F	
Middle Barrel Temperature	360 - 377 Å°C	680 - 711 Å°F	
Front Barrel Temperature	366 - 382 Å°C	691 - 720 Å°F	
Nozzle Temperature	360 - 377 Å°C	680 - 711 Å°F	
Melt Temperature	366 - 388 Å°C	691 - 730 Å°F	
Mold Temperature	107 - 163 Å°C	225 - 325 Å°F	
Drying Temperature	166 - 177 Å°C @Time 14400 sec	331 - 351 Å°F @Time 4.00 hour	

Descriptive Properties	Value	Comments
Agency Ratings	FAA FAR 25.853a; FAA FAR 25.853d	
Availability	North America	
Color	Colors Available	
Form	Pellets	
Injection Rate	Fast	
Processing Technique	Injection Molding	
Screw Compression Ratio	2.0:1.0 to 3.0:1.0	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China