

Solvay Specialty Polymers Ryton® R-7-121NA Polyphenylene Sulfide (PPS), GlassMineral Filled

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS), Mineral/Glass-Fiber Filled

Material Notes:

Ryton® R-7-121NA and R-7-121BL glass fiber and mineral filled polyphenylene sulfide compounds provide good mechanical strength with good flow and low maintenance molding using conventional molding equipment. Features: Good Flow; Good Strength Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Ryton-R-7-121NA-Polyphenylene-Sulfide-PPS-GlassMineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.95 g/cc	0.0704 lb/in ³	ASTM D792
Water Absorption	0.020 % @Time 86400 sec	0.020 % @Time 24.0 hour	ISO 62
Linear Mold Shrinkage, Flow	0.0020 cm/cm @Thickness 3.18 mm	0.0020 in/in @Thickness 0.125 in	
Linear Mold Shrinkage, Transverse	0.0040 cm/cm @Thickness 3.20 mm	0.0040 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	101	101	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength	131 MPa	19000 psi	ASTM D638
Tensile Stress	135 MPa	19600 psi	ISO 527-2
Elongation at Break	1.0 %	1.0 %	ISO 527-2
	1.0 %	1.0 %	ASTM D638
Flexural Strength	207 MPa	30000 psi	ASTM D790
	210 MPa	30500 psi	ISO 178
Flexural Modulus	17.2 GPa	2490 ksi	ASTM D790
	18.0 GPa	2610 ksi	ISO 178
Compressive Strength	285 MPa	41300 psi	ASTM D695
Poissons Ratio	0.36	0.36	ASTM E132

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	0.510 J/cm @Thickness 3.18 mm	0.37 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	2.10 J/cm @Thickness 3.18 mm	3.93 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Notched (ISO)	6.00 kJ/mÂ²	2.86 ft-lb/inÂ²	Notch A; ISO 180
Izod Impact, Unnotched (ISO)	16.0 kJ/mÂ²	7.61 ft-lb/inÂ²	ISO 180

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	15.0 Âµm/m-Â°C @Temperature 100 - 200 Â°C	8.33 Âµin/in-Â°F @Temperature 212 - 392 Â°F	2
	15.0 Âµm/m-Â°C @Temperature -50.0 - 50.0 Â°C	8.33 Âµin/in-Â°F @Temperature -58.0 - 122 Â°F	2
CTE, linear, Transverse to Flow	30.0 Âµm/m-Â°C @Temperature -50.0 - 50.0 Â°C	16.7 Âµin/in-Â°F @Temperature -58.0 - 122 Â°F	TMA; ASTM E831
	70.0 Âµm/m-Â°C @Temperature 100 - 200 Â°C	38.9 Âµin/in-Â°F @Temperature 212 - 392 Â°F	TMA; ASTM E831
Thermal Conductivity	0.580 W/m-K	4.03 BTU-in/hr-ftÂ²-Â°F	ASTM C177
Maximum Service Temperature, Air	220 - 240 Â°C	428 - 464 Â°F	UL Temperature Rating
Deflection Temperature at 1.8 MPa (264 psi)	265 Â°C	509 Â°F	Unannealed; ASTM D648
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	5VA @Thickness 1.60 mm	5VA @Thickness 0.0630 in	
Oxygen Index	61 %	61 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257

Electrical Properties	Metric	English	Comments
Insulation Resistance	1.00e+11 ohm @Temperature 90.0 Â°C	1.00e+11 ohm @Temperature 194 Â°F	IEC 60167
Dielectric Constant	4.8 @Frequency 1000 Hz	4.8 @Frequency 1000 Hz	ASTM D150
Dielectric Strength	4.9 @Frequency 1.00e+6 Hz	4.9 @Frequency 1.00e+6 Hz	ASTM D150
Dissipation Factor	18.0 kV/mm	457 kV/in	ASTM D149
	0.0020 @Frequency 1.00e+6 Hz	0.0020 @Frequency 1.00e+6 Hz	ASTM D150
	0.0040 @Frequency 60.0 Hz	0.0040 @Frequency 60.0 Hz	ASTM D150
Arc Resistance	185 sec	185 sec	ASTM D495
Comparative Tracking Index	250 V	250 V	UL 746

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	Latin America	
	North America	
Color	Natural	
Form	Pellets	
Processing Technique	Injection Molding	
RoHS Compliance	RoHS Compliant	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China