

## Solvay Specialty Polymers Tecnoflon® T 636/L Fluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

TECNOFLON® T 636/L is a low viscosity fluoroelastomer terpolymer designed to provide improved low temperature characteristics. Tecnoflon® T 636/L does not contain curatives: therefore the proper levels of Tecnoflon® FOR M1 and Tecnoflon® FOR M2 must be added to achieve the required properties. Tecnoflon® T 636/L is a lower viscosity version of Tecnoflon® T 636: please refer to Tecnoflon® T 636 Technical data sheet for data on chemical resistance: Tecnoflon® T 636/L exhibits the same excellent heat and chemical resistance expected from Tecnoflon® copolymers. Features: Good Chemical Resistance; Good Flow; Good Mold Release; High Heat Resistance; Low Compression Set; Low Viscosity; Terpolymer Uses: Belts/Belt Repair; Blending; Diaphragms; Gaskets; Hose; Low Temperature Applications; Profiles; Seals; Sheet Additional Properties: Fluorine Content - 66 % Information provided by Solvay Specialty Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Solvay-Specialty-Polymers-Tecnoflon-T-636L-Fluoroelastomer.php](http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Tecnoflon-T-636L-Fluoroelastomer.php)

Physical Properties	Metric	English	Comments
Mooney Viscosity	22 @Temperature 121 Â°C	22 @Temperature 250 Â°F	ML 1+10; ASTM D1646

Descriptive Properties	Value	Comments
Availability	Europe; North America	
Color	Translucent	
Form	Slab	
Processing Technique	Calendering; Compounding	
	Compression Molding; Extrusion	
	Injection Molding; Resin Transfer Molding	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China