

Solvay TECHNYL® C 216 V15 PA6, 15% glass filled, Eh 0

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Glass Fiber Filled

Material Notes:

Description: TECHNYL C 216 V15 is a polyamide 6 with 15% of glass fiber. Colors: it is marketed in the black color and natural. Available in: Asia Pacific and Europe

Main Properties: Dimensional stability, Impact resistance and Stiffness

Applications: TECHNYL C 216 V15 was developed for applications on parts where good mechanical properties as impact resistance, superficial aspect and dimensional stability are required. Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-TECHNYL-C-216-V15-PA6-15-glass-filled-Eh-0.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ISO 1183/A
Water Absorption	1.15 % @Temperature 23.0 °C, Time 86400 sec	1.15 % @Temperature 73.4 °F, Time 24.0 hour	ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	ISO R 527
Elongation at Break	4.0 %	4.0 %	ISO R 527
Tensile Modulus	6.10 GPa	885 ksi	ISO R 527
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180/1eA
Charpy Impact Unnotched	4.20 J/cm ²	20.0 ft-lb/in ²	ISO 179/1eU
Charpy Impact, Notched	0.550 J/cm ²	2.62 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	222 °C	432 °F	
Deflection Temperature at 1.8 MPa (264 psi)	180 °C	356 °F	ISO 75-2
Flammability, UL94	HB	HB	
Oxygen Index	23 %	23 %	ISO 4589
Glow Wire Test	650 °C @Thickness 1.60 mm	1200 °F @Thickness 0.0630 in	CEI 695

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	CEI 93
Dielectric Constant	3.8	3.8	CEI 250
Dissipation Factor	0.020	0.020	CEI 250
Comparative Tracking Index	550 V	550 V	CEI 112

Processing Properties	Metric	English	Comments
Feed Temperature	225 - 230 Â°C	437 - 446 Â°F	
Nozzle Temperature	230 - 240 Â°C	446 - 464 Â°F	
Mold Temperature	80.0 - 100 Â°C	176 - 212 Â°F	

Descriptive Properties	Value	Comments
Compression Zone	230-240Â°C	
Mixing Zone	230-240Â°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China