

Solvay TECHNYLÂ® eXten D 458P PA6.10, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 610

Material Notes:

Description: Product in development - provisional datasheet. High viscosity unfilled plasticized PA6.10 for extrusion applications providing low end part warpage. Available in: Asia Pacific, Europe, Latin America and North America Product Applications: Polyamide 6,10 for extrusion, where high flexibility and toughness are requested, especially low temperature toughness. TECHNYLÂ® eXten D 458P is specially developed for automotive and other applications where a long term high temperature usage is requested. This material is available in black and natural. Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-TECHNYL-eXten-D-458P-PA610-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/inÂ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	34.0 MPa	4930 psi	ISO 527 Type 1A
Elongation at Break	240 %	240 %	ISO 527 Type 1A
Tensile Modulus	0.550 GPa	79.8 ksi	ISO 527 Type 1A
Flexural Strength	22.0 MPa	3190 psi	ISO 178
Flexural Modulus	0.530 GPa	76.9 ksi	ISO 178
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
Charpy Impact, Notched	1.90 J/cmÂ²	9.04 ft-lb/inÂ²	ISO 179/1eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
	11.7 J/cmÂ²	55.7 ft-lb/inÂ²	ISO 179/1eA
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Melting Point	215 Â°C	419 Â°F	ISO 11357

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.10 %	<= 0.10 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China