

Star Plastics ABS5035 Molding Grade ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Information provided by Star Plastics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Star-Plastics-ABS5035-Molding-Grade-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Maximum Moisture Content	0.15	0.15	
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D955
Melt Flow	5.0 g/10 min @Load 3.80 kg, Temperature 230 Â°C	5.0 g/10 min @Load 8.38 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	40.0 MPa	5800 psi	ASTM D638
Tensile Modulus	2.00 GPa	290 ksi	ASTM D638
Flexural Yield Strength	58.6 MPa	8500 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	1.87 J/cm	3.50 ft-lb/in	73Â°F, 0.125 in.; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	76.7 Â°C	170 Â°F	unannealed, .125in; ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	188 - 218 Â°C	370 - 425 Â°F	
Middle Barrel Temperature	204 - 232 Â°C	400 - 450 Â°F	
Front Barrel Temperature	218 - 246 Â°C	425 - 475 Â°F	
Nozzle Temperature	218 - 274 Â°C	425 - 525 Â°F	
Melt Temperature	218 - 274 Â°C	425 - 525 Â°F	

Processing Properties	Metric	English	Comments
Drying Temperature	82.2 - 93.3 Â°C	180 - 200 Â°F	
Dry Time	2 - 4 hour	2 - 4 hour	
Back Pressure	0.172 - 0.689 MPa	25.0 - 100 psi	
Screw Speed	25 - 75 rpm	25 - 75 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China