

Star Plastics PCGF10 Molding Grade PC with 10% Glass

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 10% Glass Filled

Material Notes:

Information provided by Star Plastics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Star-Plastics-PCGF10-Molding-Grade-PC-with-10-Glass.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955
Melt Flow	15 g/10 min @Load 1.20 kg, Temperature 300 Â°C	15 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.5 MPa	9500 psi	ASTM D638
Tensile Modulus	3.10 GPa	450 ksi	ASTM D638
Flexural Yield Strength	100 MPa	14500 psi	ASTM D790
Flexural Modulus	3.10 GPa	450 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	73Â°F, 0.125 in.; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	135 Â°C	275 Â°F	unannealed, .125in; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	288 - 316 Â°C	550 - 600 Â°F	
Middle Barrel Temperature	302 - 329 Â°C	575 - 625 Â°F	
Front Barrel Temperature	316 - 343 Â°C	600 - 650 Â°F	
Nozzle Temperature	316 - 343 Â°C	600 - 650 Â°F	
Melt Temperature	316 - 343 Â°C	600 - 650 Â°F	
Mold Temperature	10.0 - 93.3 Â°C	50.0 - 200 Â°F	

Processing Properties	Metric	English	Comments
Dry Time	4 hour	4 hour	
Back Pressure	0.276 - 0.689 MPa	40.0 - 100 psi	
Screw Speed	25 - 75 rpm	25 - 75 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China