

Star Plastics PC/PBTQX7008 Molding Grade PC/PBT

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Information provided by Star Plastics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Star-Plastics-PCPBTQX7008-Molding-Grade-PCPBT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	
Linear Mold Shrinkage	0.0080 - 0.011 cm/cm	0.0080 - 0.011 in/in	ASTM D955
Melt Flow	7.0 g/10 min @Load 3.80 kg, Temperature 230 Â°C	7.0 g/10 min @Load 8.38 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	47.6 MPa	6900 psi	ASTM D638
Tensile Modulus	1.65 GPa	240 ksi	ASTM D638
Flexural Yield Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	1.76 GPa	255 ksi	ASTM D790
Izod Impact, Notched	6.67 J/cm	12.5 ft-lb/in	73Â°F, 0.125 in.; ASTM D256
	2.40 J/cm @Temperature -28.9 Â°C	4.50 ft-lb/in @Temperature -20.0 Â°F	0.125in

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	98.9 Â°C	210 Â°F	unannealed, .125in; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	243 - 271 Â°C	470 - 520 Â°F	
Middle Barrel Temperature	249 - 277 Â°C	480 - 530 Â°F	
Front Barrel Temperature	257 - 282 Â°C	495 - 540 Â°F	

Nozzle Temperature Processing Properties	254 - 274 Â°C Metric	490 - 525 Â°F English	Comments
Melt Temperature	260 - 279 Â°C	500 - 535 Â°F	
Mold Temperature	65.6 Â°C	150 Â°F	
Drying Temperature	121 Â°C	250 Â°F	
Dry Time	4 hour	4 hour	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Screw Speed	40 - 75 rpm	40 - 75 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China