

Styrolution Luran® SAN 51 Styrene Acrylonitrile

Category : Polymer , Thermoplastic , SAN Polymer , Styrene Acrylonitrile (SAN), Transparent

Material Notes:

Luran SAN 51 is an injection molding grade of SAN with excellent chemical resistance and toughness. Information provided by Styrolution

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Luran-SAN-51-Styrene-Acrylonitrile.php

Physical Properties	Metric	English	Comments
Melt Flow	15 g/10 min	15 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	106 °C	223 °F	120°C/h; ASTM D 1525
	@Load 5.10 kg	@Load 11.2 lb	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China