

Styrolution Novodur® 4140PG ABS

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Novodur Ultra 4140PG is a PC modified plating grade combining high heat resistance and excellent impact strength with the unique surface properties of a Novodur ABS material. Information provided by Styrolution

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Novodur-4140PG-ABS.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ISO 294-4
Melt Flow	9.0 g/10 min	9.0 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	
	13 g/10 min	13 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 260 °C	@Load 11.0 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	85.0 MPa	12300 psi	ISO 2039-1
Tensile Strength, Yield	46.0 MPa	6670 psi	ISO 527
Elongation at Yield	3.5 %	3.5 %	ISO 527
Tensile Modulus	2.10 GPa	305 ksi	ISO 527
Flexural Strength	72.0 MPa	10400 psi	ISO 178
Flexural Modulus	2.10 GPa	305 ksi	ISO 178
Izod Impact, Notched (ISO)	31.0 kJ/m ²	14.8 ft-lb/in ²	ISO 180/A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	40.0 kJ/m ²	19.0 ft-lb/in ²	ISO 180/A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	2.80 J/cm ²	13.3 ft-lb/in ²	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	3.80 J/cm ²	18.1 ft-lb/in ²	

Mechanical Properties	Metric	English	Comments
	@ Temperature 23.0 Â°C	@ Temperature 73.4 Â°F	ISO 178

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 Âµm/m-Â°C	50.0 Âµin/in-Â°F	ISO 11359
Deflection Temperature at 0.46 MPa (66 psi)	108 Â°C	226 Â°F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	99.0 Â°C	210 Â°F	ISO 75
Vicat Softening Point	106 Â°C @Load 5.10 kg	223 Â°F @Load 11.2 lb	50Â°C/h; ISO 306

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	3.0 @Frequency 100 Hz	3.0 @Frequency 100 Hz	IEC 60250
Dielectric Strength	37.0 kV/mm @Thickness 1.50 mm	940 kV/in @Thickness 0.0591 in	Short Time; IEC 60243-1
Dissipation Factor	0.0040 @Frequency 100 Hz	0.0040 @Frequency 100 Hz	IEC 60250
	0.0085 @Frequency 1.00e+6 Hz	0.0085 @Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 270 Â°C	446 - 518 Â°F	ISO 294
Mold Temperature	70.0 Â°C	158 Â°F	ISO 294
Injection Velocity	240 mm/sec	9.45 in/sec	ISO 294
Drying Temperature	80.0 Â°C @Time 7200 - 14400 sec	176 Â°F @Time 2.00 - 4.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China