

Styron Magnum® 341 ABS, Low Gloss

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

MAGNUM® ABS resins are thermoplastic materials which provide an excellent balance of processability, impact resistance and heat resistance as imparted by the various polymer compositions. MAGNUM ABS resin are available in a wide range of melt flow rates, impact strength and heat resistance for both high and low gloss applications manufactured by injection molding, sheet or profile extrusion and thermoforming. MAGNUM ABS resins offer a wide range of processability and impact resistance for low gloss injection molding applications. Combined with heat resistance and tensile and flexural strength, MAGNUM ABS resins are used in a wide variety of injection molding applications. MAGNUM 341 ABS resin is a low gloss, low impact strength resin with good processability. Data provided by Dow Chemical. This product line was spun off from Dow Chemical to Styron in 2010.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styron-Magnum-341-ABS-Low-Gloss.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM Data
Linear Mold Shrinkage	0.0055 cm/cm	0.0055 in/in	
Melt Flow	5.0 g/10 min @Load 3.80 kg, Temperature 230 °C	5.0 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM Data

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	41.4 MPa	6000 psi	ASTM Data
Tensile Strength, Yield	49.6 MPa	7190 psi	ASTM Data
Elongation at Yield	2.7 %	2.7 %	ISO Data
Tensile Modulus	2.48 GPa	360 ksi	ASTM Data
Izod Impact, Notched	1.50 J/cm	2.81 ft-lb/in	ASTM Data
Charpy Impact Unnotched	8.00 J/cm ²	38.1 ft-lb/in ²	ISO Data, Low Temp
	NB	NB	ISO Data
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO Data, Low Temp
	1.70 J/cm ²	8.09 ft-lb/in ²	ISO Data
Impact Test	43.0 J @Temperature 23.0 °C	31.7 ft-lb @Temperature 73.4 °F	Instrumented Dart Total Energy

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	79.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	43.9 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ISO data
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	76.0 $^{\circ}\text{C}$	169 $^{\circ}\text{F}$	Unannealed; ASTM Data
Vicat Softening Point	105 $^{\circ}\text{C}$	221 $^{\circ}\text{F}$	
Flammability, UL94	HB	HB	
	@Thickness 1.47 mm	@Thickness 0.0579 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China