

Sumitomo Chemical ESPOLEX® UT412A Thermoplastic Elastomer

Category: Polymer, Thermoplastic, Elastomer, TPE

Material Notes:

ESPOLEX® TPE Series is a group of thermoplastic elastomers produced by Sumitomo Chemical Company. Among its material advantages, ESPOLEX® TPE Series is distinguished by offering many low-density grades that can provide substantial weight and cost savings over higher-density thermoplastic elastomers. In this regard, SUMITOMO CHEMICAL introduces specific gravity as a significant factor in reducing unit cost and weight. Products molded from ESPOLEX® TPE Series exhibit rubber-like properties that range from a soft elastic to a semi-hard rubber material. Like all thermoplastic elastomers, ESPOLEX® TPE Series offers substantial savings over thermoset rubber in manufacturing since it is processed using standard thermoplastic processing equipment and techniques, and it does not require the vulcanization required by conventional rubbers. Information provided by Sumitomo Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sumitomo-Chemical-ESPOLEX-UT412A-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Density	0.880 g/cc	0.0318 lb/in³	ASTM D792
Melt Flow	4.5 g/10 min	4.5 g/10 min	ASTM D1238
	@Load 2.20 kg	@Load 4.86 lb	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93	93	10 Sec Delay; ASTM D2240
	96	96	0 Sec Delay; ASTM D2240
Hardness, Shore D	35	35	10 Sec Delay; ASTM D2240
	48	48	0 Sec Delay; ASTM D2240
Tensile Strength at Break	13.0 MPa	1890 psi	ASTM D412
Elongation at Break	550 %	550 %	ASTM D412
Flexural Modulus	0.250 GPa	36.3 ksi	ASTM D790
Tear Strength	89.0 kN/m	508 pli	ASTM D624

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	200 - 245 °C	392 - 473 °F	
Mold Temperature	30.0 - 50.0 °C	86.0 - 122 °F	

Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China