

TIMET TIMETAL® 21S Titanium Alloy (Ti-15Mo-3Nb-3Al-0.2Si, ASTM Grade 21); Annealed Strip/Sheet

Category : Metal , Nonferrous Metal , Titanium Alloy , Beta Titanium Alloy

Material Notes:

High-Strength, Oxidation Resistant Strip Alloy Features: Offers the good cold formability and weldability of a beta strip alloy, but with greatly improved oxidation resistance and creep strength. Aerospace applications include engine exhaust plug and nozzle assemblies. The alloy's resistance to aircraft hydraulic fluids, such as Skydrol, is excellent at all temperatures. It is well suited for metal matrix composites because it can be economically rolled to foil, is compatible with most fibers, and is sufficiently stable up to 816°C. Typical heat treatment for this alloy: Solution treatment: 816-843°C for 3-30 min, air cool. Age treatment: 510-679°C for 8-16 hrs. Data provided by TIMET.

Order this product through the following link:

http://www.lookpolymers.com/polymer_TIMET-TIMETAL-21S-Titanium-Alloy-Ti-15Mo-3Nb-3Al-02Si-ASTM-Grade-21-Annealed-StripSheet.php

Physical Properties	Metric	English	Comments
Density	4.94 g/cc	0.178 lb/in ³	Typical

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	915 MPa	133000 psi	Typical
Tensile Strength, Yield	880 MPa @Strain 0.200 %	128000 psi @Strain 0.200 %	Typical
Elongation at Break	15 %	15 %	Typical
Modulus of Elasticity	83.0 GPa	12000 ksi	Typical
Bend Radius, Minimum	2.5 t	2.5 t	Typical; on 0.078 in (2 mm) sheet

Thermal Properties	Metric	English	Comments
CTE, linear	7.07 µm/m-°C	3.93 µin/in-°F	
	@Temperature 38.0 °C	@Temperature 100 °F	
	8.90 µm/m-°C	4.94 µin/in-°F	
	@Temperature >=316 °C	@Temperature >=601 °F	
	9.50 µm/m-°C	5.28 µin/in-°F	
	@Temperature 538 °C	@Temperature 1000 °F	
Specific Heat Capacity	0.490 J/g-°C	0.117 BTU/lb-°F	
Thermal Conductivity	7.60 W/m-K	52.7 BTU-in/hr-ft ² -°F	

Maximum Service Temperature, Air Thermal Properties	593 °C Metric	1100 °F English	Structural Applications Comments
	816 °C	1500 °F	Use in metal matrix composites
Beta Transus	800 °C	1470 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	2.5 - 3.5 %	2.5 - 3.5 %	
Carbon, C	<= 0.050 %	<= 0.050 %	
Hydrogen, H	<= 0.015 %	<= 0.015 %	
Iron, Fe	<= 0.40 %	<= 0.40 %	
Molybdenum, Mo	14 - 16 %	14 - 16 %	
Niobium, Nb (Columbium, Cb)	2.4 - 3.2 %	2.4 - 3.2 %	
Nitrogen, N	<= 0.050 %	<= 0.050 %	
Oxygen, O	0.11 - 0.17 %	0.11 - 0.17 %	
Silicon, Si	0.15 - 0.25 %	0.15 - 0.25 %	
Titanium, Ti	76 - 80.8 %	76 - 80.8 %	Calculated as remainder

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000135 ohm-cm	0.000135 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China