

TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 20 PHR Non-Black, Soft Clay

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Formulation Millathane 76 100.0 Zinc Stearate 0.5 Poly AC 617A 1.0 MBTS 4.0 MBT 2.0 Thanecure® ZM1.0 TP-95 10.0 Sulfur 2.0 Soft Clay 20 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-20-PHR-Non-Black-Soft-Clay.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	
Tensile Strength, Yield	26.92 MPa	3905 psi	
Elongation at Yield	677 %	677 %	
100% Modulus	0.00136 GPa	0.197 ksi	
200% Modulus	0.00234 GPa	0.340 ksi	
300% Modulus	0.00358 GPa	0.519 ksi	
Tear Strength	43.4 kN/m	248 pli	
Taber Abrasion, mg/1000 Cycles	14 @Load 1.00 kg	14 @Load 2.20 lb	H-18 wheel
Compression Set	45.1 % @Temperature 70.0 °C, Time 79200 sec	45.1 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min @Temperature 155 °C	0.167 hour @Temperature 311 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China