

TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 310°F Cure Temperature

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Formulation Millathane 76 100.0 Zinc Stearate 0.5 N-330 Black 30.0 Cumar P-10 10.0 MBTS 4.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 1.5 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-310F-Cure-Temperature.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	
Tensile Strength, Yield	33.05 MPa	4793 psi	
Elongation at Break	687 %	687 %	
Tear Strength	65.1 kN/m	371 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	10.0 min	0.167 hour	
	@Temperature 154 °C	@Temperature 310 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China