

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, Hardness 60A, Non-Black Sulfur Cure

**Category :** Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Formulation Millathane 76 100.0 Zinc Stearate 0.5 Translink 55530.0 TP-955.0 MBTS 4.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 2.0 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-Hardness-60A-Non-Black-Sulfur-Cure.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-Hardness-60A-Non-Black-Sulfur-Cure.php)

| Mechanical Properties   | Metric       | English   | Comments |
|-------------------------|--------------|-----------|----------|
| Hardness, Shore A       | 60           | 60        |          |
| Tensile Strength, Yield | 30.43 MPa    | 4413 psi  |          |
| Elongation at Yield     | 502 %        | 502 %     |          |
| 100% Modulus            | 0.00314 GPa  | 0.455 ksi |          |
| 200% Modulus            | 0.009067 GPa | 1.315 ksi |          |
| 300% Modulus            | 0.01631 GPa  | 2.366 ksi |          |
| Tear Strength           | 66.6 kN/m    | 380 pli   | Die C    |

| Processing Properties | Metric              | English             | Comments |
|-----------------------|---------------------|---------------------|----------|
| Cure Time             | 10.0 min            | 0.167 hour          |          |
|                       | @Temperature 155 °C | @Temperature 311 °F |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China