

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber

Category: Polymer, Thermoset, Polyester, TS, Polyurethane, TS, Thermoset Polyurethane, Elastomer, Unreinforced, Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

Millathane 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications — bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires — and many other high performance polyurethane applications. All information provided by TSE Industries

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	
Mooney Viscosity	25 - 45	25 - 45	Standard; ML(1+4)
	@Temperature 100 °C	@Temperature 212 °F	
	25 - 70	25 - 70	ML(1+4)
	@Temperature 100 °C	@Temperature 212 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30 - 90	30 - 90	
Tensile Strength, Yield	31.0 MPa	4500 psi	
Elongation at Yield	500 %	500 %	
Resilience	10 - 20	10 - 20	%

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-40.0 °C	-40.0 °F	

Descriptive Properties	Value	Comments
Appearance	Light to dark amber solid bale or milled sheets	
Compression Set	Very Good	Peroxide Cure
Health Hazard	None	
Heat Aging Resistance	Good at 100°C	sulfur cure
	Very Good at 100°C	peroxide cure
Ozone Resistance	Excellent	



Descriptive Properties	Screllent Value	Comments
Tear Resistance	Very Good	Sulfur Cure
Weather Resistance	Good	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China