

TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with 20 PHR N330 (HAF) Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100.0 Zinc Stearate 0.5 Struktol WB 2220.5 Poly AC 617A 0.5 Cumar P1010.0 MBTS 4.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 1.5 Carbon Black N-330 (HAF) 20 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-20-PHR-N330-HAF-Filler.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	>= 60	>= 60	
Tensile Strength, Yield	32.39 MPa	4698 psi	
Elongation at Yield	578 %	578 %	
100% Modulus	0.00210 GPa	0.305 ksi	
200% Modulus	0.00420 GPa	0.609 ksi	
300% Modulus	0.007598 GPa	1.102 ksi	
Tear Strength	39.9 kN/m	228 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	10.0 min	0.167 hour	Press cured
	@Temperature 68.3 °C	@Temperature 155 °F	

Descriptive Properties	Value	Comments
DIN Abrasion (mm³)	40	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China