

TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with 4.0 PHR MBTS

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100 Zinc Stearate 0.5 N330 Black 30.0 Cumar P10 10.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 1.5 MBTS 4.0 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-40-PHR-MBTS.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	>= 65	>= 65	
Tensile Strength, Yield	30.19 MPa	4379 psi	
Elongation at Yield	559 %	559 %	
100% Modulus	0.00270 GPa	0.392 ksi	
200% Modulus	0.00580 GPa	0.841 ksi	
300% Modulus	0.01030 GPa	1.494 ksi	
Tear Strength	35.0 kN/m	200 pli	Die C
Compression Set	32.2 % @Temperature 70.0 °C, Time 79200 sec	32.2 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min @Temperature 155 °C	0.167 hour @Temperature 311 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China