

TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with 60 PHR Hi-Sil 233 Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100.0 Zinc Stearate 0.5 MBTS 4.0 MBT 2.0 Thane cure® ZM1.0 Sulfur 1.5 Cumar P10 10.0 Precipitated Silica - Hi-Sil 23360 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-60-PHR-Hi-Sil-233-Filler.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	>= 78	>= 78	
Tensile Strength, Yield	25.1 MPa	3640 psi	
Elongation at Yield	760 %	760 %	
100% Modulus	0.00200 GPa	0.290 ksi	
200% Modulus	0.00320 GPa	0.464 ksi	
300% Modulus	0.00480 GPa	0.696 ksi	
Tear Strength	32.5 kN/m	185 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	16.0 min	0.267 hour	Press cured
	@Temperature 68.3 °C	@Temperature 155 °F	

Descriptive Properties	Value	Comments
DIN Abrasion (mm³)	65.3	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China