

Taiwan PU Corporation CPU-69-A/B Mixing Ratio 100/30 Polyurethane Casting Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Compound of CPU-69-A/B with a mixing ratio of 100/30 Information provided by Taiwan PU Corporation. MatWeb has a separate entry for the unmixed A and B components.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-CPU-69-AB-Mixing-Ratio-10030-Polyurethane-Casting-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	66	66	
Tensile Strength at Break	8.53 MPa	1240 psi	
Elongation at Break	425 %	425 %	
Tear Strength	23.5 kN/m	134 pli	

Descriptive Properties	Value	Comments
Mixing Ratio	100/30	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China