

Taiwan PU Corporation TPU-E95 General Grade, Extrusion Molding Polyester Base TPU

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Thermoplastic Polyurethane (TPU), General Grade, Polyester Base, Extrusion Molding Information provided by Taiwan PU Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-TPU-E95-General-Grade-Extrusion-Molding-Polyester-Base-TPU.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	95	95	
Tensile Strength at Break	41.19 MPa	5974 psi	
Elongation at Break	700 %	700 %	
100% Modulus	0.0103 GPa	1.49 ksi	
300% Modulus	0.0206 GPa	2.99 ksi	
Resilience	30	30	%, Impact Resilience
Taber Abrasion, mg/1000 Cycles	6.0	6.0	

Processing Properties	Metric	English	Comments
Feed Temperature	195 Â°C	383 Â°F	
Middle Barrel Temperature	200 Â°C	392 Â°F	Compress zone
Front Barrel Temperature	205 Â°C	401 Â°F	Metering zone
Adapter Temperature	210 Â°C	410 Â°F	
Die Temperature	210 Â°C	410 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China